CB12120

NON-SPILLABLE RECHARGEABLE SEALED LEAD ACID BATTERY




FEATURES


- AGM valve regulated sealing technology;
- High strength ABS material for container & lid;
- Wide temperature scope of application (-15~45°C);
- Best temperature of application (20±5°C);
- No leaking, safe and reliable;
- Standing or lying down for using, convenient to transport and install;
- High sealed reaction efficiency, little loss of water, no need to add distilled water or electrolyte, simple to use and maintain;
- Low self-discharge rate.

SPECIFICATIONS

DIMENSION



TERMINAL



Nominal Voltage	12V		C ₂₀	12.0Ah (10.5V, at 25°C)	
Nominal Capacity (C ₂₀)	12Ah(10.5V, at 25°C)	Consitu	C ₁₀	10.8Ah (10.5V, at 25°C)	
	Length 151mm	Capacity	C ₃	9.0Ah (10.5V, at 25℃)	
Dimension	Width 98mm		C ₁	7.2Ah (10.2V, at 25°C)	
	Height 94.5mm	Internal Resistance		Approx. 14 mΩ (25°C)	
	Total Height 100mm	Max Short-duration Dis		vischarge Current	360A(25℃)
Weight	Approx. 3.85kg	Terminal		FO-02/FO-03/ FO-12	

CB12120

NON-SPILLABLE RECHARGEABLE SEALED LEAD ACID BATTERY

CHARGE


Using Mode	Charging Voltage	Temperature Compensation	Max Charging Current	
Standby Use2.275±0.025V/cell (25°C)		-3.3mV/°C/cell	3.6A	
Cyclic Use 2.45±0.05V/cell (25°C)		-5mV/°C/cell		


STORAGE

- Batteries should be stored in dry and clean warehouse which has good air exchange system. Batteries should avoid direct sunlight. Batteries should not be near to heat (such as radiator, the distance should more than 1m). Batteries should avoid any toxic gas and organic solvent.
- When the ambient temperature is less than 25° , the longest storage life is 6 months. If ambient temperature is higher, the longest storage life varies as specified in below chart.


Storage Temperature ($^{\circ}$ C)	≤25	26~33	34~40
Storage Time (Month)	6	3	1


• Batteries should be recharged within the storage life or before using. Charging methods: maximum charging current 3.6A, constant voltage 2.45 ± 0.05 V/cell (25° C); Charging time: 15~20h; Temperature compensation coefficient: -5mV/°C/cell.





Add: No.172, Checheng Road, Wuhan Economic & Technology Development Zone, Wuhan, China, 430056. Tel: (86)27-8489 1318 Fax: (86)27-8489 1924 E-mail: sales@cgbbattery.com





WUHAN CHANGGUANG BATTERY CO., LTD. www.cgb.com.cn